

EXPERT 75WS – 75 g/m² Window Sign

Expert 75WS is a 75gsm highly developed, printable adhesive construction for window signage. It is perfectly optimized for dry toner print applications. The lightly textured paper face enables a vibrant image and excellent toner bonding.



Physical characteristics

Property	Typical Value	Unit	Test Method
Total Thickness	215 +/- 6	μ	Electronic micrometer
Total Weight	232 +/- 6	g/m2	Internal method
Paper Face Thickness	132 +/- 4	μ	Electronic micrometer
Liner Film Thickness	53 +/- 2	μ	Electronic micrometer
Adhesive Application Temperature	+5 to +50	°C	Internal Method
Adhesive Service Temperature	-20 to +60	°C	Internal Method

Availability Sheets/Pack

A4	100/500
----	---------

Recommended conditions

For use	10° C – 30° C, 40% - 55% RH
For storage	10° C – 20° C, 20% - 55% RH
Shelf life	24 months after delivery (under recommended storage conditions)

Compatibility

Suitable for most thermal transfer and dry toner (laser/LED/flash fusion) print processes, both mono and colour small-volume, mid-volume & production machines. On such machines the user must establish for themselves the optimum settings and paper path, being aware of the thickness and weight of the material. The printable surface is also suitable for screen print, offset litho (using only fully oxidising inks).

Applications and characteristics:

It has a smooth matt surface giving a strong dense image with excellent print adhesion.

Instructions: It is printable on the paper side, is applied inside thanks to the strippable border which reveal a clear adhesive liner, and allows for the printed graphic to be viewed from outside. Easily applied to windows with excellent repositionability & removability.

- ✓ Water resistant, wipeable and punchable.
- ✓ Ideal for windows graphics, signage and displays
- ✓ Replaces the need for paper to be printed and then encapsulated.

NOTICE The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.