



EXPERT 26H – 260g/m² Horizontal Pre-Fold Matt Film

Expert 26H is a 260gsm 2-side matt aqueous coated polyester film with a horizontal pre-fold, optimised for Production & Digital Press print applications.



CExample Price	es of phon	Greenbank	
Germany			1
Day Time	Smirules	£5.60	
Evering	Sminutes	£5.40	
Testanda	5 minutes	64.80	
America			
DayTime	Sminutes	64.85	
During	5 minutes	66.60	14
Testants	5 minutes	64.40	1
Australia			por l
Day Tina Tanay Residence	5 minutes 5 minutes 5 minutes	13.80 13.40 17.40	TELEPHONE DIRECTORY
The second secon	THE OF THE ADDRESS OF	for all calls	TELEPHONE The second second second Second second se

Physical characteristics

Property	Typical Value	Unit	Test Method
Weight	261 +/- 6	g /m2	Internal Method
Thickness	193 +/- 5	μ	Electronic Micrometer
Opacity	>98	%	TAPPI T519
CIE Whiteness	>140	CIE WI	ASTM E313 DCI Spectraflash (D65, 10° observer, UV incl.)
Melting Point	250	°C	ASTM E794-85
Usage Temperature -40 - +120		°C	Internal method

Availabilit	y Sheets/Pack	Compatibility	
A4	100/500	Suitable for most thermal transfer and dry toner (laser/LED/flash fusion) prir processes, both mono and colour small-volume, mid-volume & productio	
Recommended conditions		machines. On such machines the user must establish for themselves the optimum settings and paper path, being aware of the thickness and weight of the material.	
For use	10°C - 30°C, 40% - 55% RH	The printable surface is also suitable for screen print, offset litho (using only full oxidising inks).	
For storage	10°C - 20°C, 20% - 55% RH	Applications and characteristics: It has a smooth matt surface giving a strong dense image with	
Shelf Life	24 months after delivery (under recommended storage conditions)	 excellent print adhesion and can be printed on both sides where equipment allows. ✓ Water resistant, wipeable and punchable. ✓ Ideal for instant landscape style menus. 	
		\checkmark Replaces the need for paper to be printed and then	

NOTICE The information provided herein is correct to the best of our knowledge. No liability for any errors, facts or opinions is accepted. You must satisfy yourself as to the suitability of this product for your application. No responsibility for any loss as a result of any person placing reliance on any material contained herein can be accepted.

encapsulated.